

HYDRO PRIME

EPOXY PRIMER AND MOISTURE BARRIER

TECHNICAL DATA SHEET

Hydro Prime is a two component water based epoxy compound used as both a primer and moisture barrier.

Hydro Prime is specially designed to prevent rising damp through cement and concrete surfaces.

Hydro prime can be applied onto damp surfaces and over freshly laid concrete (green concrete), screeds and renders with excellent resistance to hydrostatic pressure.

- **Two component system**
- **Excellent resistance to hydrostatic pressure.**
- **Commercial and residential work**
- **Able to be applied to damp surfaces.**
- **Easy water clean up**



Low VOC content which easily meets Green Building Council of Australia Green Star IEQ-13 requirements.

novatex
new generation building products

Novatex Products Pty Ltd
ABN:55 003 032 328
P O Box 7123
Wetherill Park NSW 2164



Telephone: 029757 3525
Facsimile: 02 9757 3454
Email: info@novatexproducts.com.au
Website: www.novatexproducts.com.au

HYDRO PRIME

EPOXY PRIMER AND MOISTURE BARRIER

Designed for fixing

Suitable for wall and floor applications for internal, external, underground and immersed areas as a primer or protective coating. Compatible surface for bonding Novatex coatings and adhesives. Maximum negative pressure 25m head of water.

Substrates

Concrete, renders, screeds, green concrete, blockwork, masonry, stone and timber surfaces.

Preparation

Ensure surfaces are sound and free from movement, oil, grease, wax, dust, any curing and release agents and any other barrier materials. Smooth or polished concrete should be prepared by mechanical abrasion to promote optimal adhesion. Where waterproofing against negative pressure or rising damp applications, efflorescence must be removed from the surface to enable maximum adhesion strength and resistance to hydrostatic pressure.

Concrete & Cement Render Screeds

Hydro Prime can be applied over freshly laid concrete (green concrete), screeds and renders. These areas must be free of surface water before application. Cannot be applied over pooled water on the surface. If applying over dried surfaces, such as aged concrete, application of a water mist over the area is recommended to lightly dampen the surface.

Plaster Board /Fibre Cement Sheet Wall and Floor

Fibre cement sheets must be suitable for the application and be fixed in accordance with the manufacturer's specifications and the relevant standards.

Compressed fibre cement sheets must be suitable for the application and be fixed in accordance with the manufacturer's specifications and the relevant standards.

Plasterboard sheets must be suitable for the application and be fixed in accordance with the manufacturer's specifications and the relevant standards.

Existing Tiles

Tiles need to be sound and clean. Remove all cracked, drummy and otherwise unsound tiles and repair appropriately. Prime surfaces using Optimus Primer. Contact Novatex Products before commencing if in doubt about required surface preparation.

Mixing

Both part A and part B should be stirred lightly to ensure a homogenous mixture before commences.

Measure by volume, add equal part A and part B into a clean pail or mixing container. Thoroughly mix the two components for approx. 3 minutes until the mixture is homogenous with a uniform colour. Mixing is done at low to medium speed to ensure correct blending. Allow Hydro Prime to settle for 5-10 minutes after mixing before using.

Application

Best results always achieved with 2 coats. For rising damp or prevention of efflorescence, a minimum 1 coat application may suffice at 3.0m²/litre. For waterproofing or creating a moisture protective barrier on the negative side of walls, then a minimum of 2 coats is recommended at 3.0m²/litre per coat. Attention and care should be taken to ensure a uniform application and required coverage is achieved. If the recommended coverage hasn't been achieved in 2 coats, then further coats should be applied until the recommended coverage is formed.

First coat can be diluted; this is dependent upon surface porosity. 5% dilution is recommended on porous surfaces.

When applying over non porous surfaces prime using Optimus Primer (Refer to you nearest Novatex office for correct application.)

Dilution should only happen with the first coat; the second coat must not be diluted.



HYDRO PRIME

EPOXY PRIMER AND MOISTURE BARRIER

Application (cont.)

Once applied, allow 24 hours curing before the application of membranes, adhesives, mortar, levelling compounds or other coatings. Curing will be prolonged in cooler temperatures and in high humidity. It is not recommended to leave Hydro Prime for more than 5 days before covering over with tiles or self-levelling compound.

Coverage

The coverage will vary depending on substrate, site conditions and application.

Packaging

Hydro Prime comes as an 8 Litre or 20 Litre kit.

Shelf Life

Hydro Prime when stored in a cool, dry environment in original pails will have a shelf life of 12 months.

Pot Life

Once A & B are mixed, the mixture must be used within 2 hours.

Clean up

Clean all equipment, surfaces etc. with soapy water while still wet.

Do not rinse product down stormwater drains or sewers.

Precautions

Gloves and eye protection should be used when handling this material.

Keep containers in well ventilated areas, ensuring lids are correctly secured. Ensure adequate ventilation while using and avoid inhalation of any vapours. Avoid spillage into water courses, drains where possible. For applications/situations not mentioned contact Novatex office.

The manufacturer is not responsible for any loss or damage arising from incorrect use. The use of this product is beyond the control of the manufacturer and liability is restricted to the replacement of material proven faulty.

Manual Handling

Manual handling of this pail without due care and attention may result in personal injury.

Technical Data

Appearance	Wet-part A-Grey; Part b-white. Dried-semi gloss, matt when aged
Re Coat	4 hours @ 20°C
Dry time	7.5hrs @ 20°C
Complete Cure time	7 days @25°C
Coverage	3.0m ² /litre
Volume solids	48%
Mixing ratio	1:1
Dry film thickness	0.3mm
Wet film thickness	300 micron/0.3mm per coat
Pot Life	1 to 2 hours@25°C
VOC	9 grams/litre
Water Vapour Transmission ASTM E96	15g/m ² ; 9g/m ² 2 coats (300 micron/0.3mmFTS)
Adhesion to concrete ASTM 4541	8N/mm ²

Contact Us

For further technical information, please contact Novatex Products on 02 9757 3525.

novatex
new generation building products

Novatex Products Pty Ltd
ABN:55 003 032 328
P O Box 7123
Wetherill Park NSW 2164



Telephone: 029757 3525
Facsimile: 02 9757 3454
Email: info@novatexproducts.com.au
Website: www.novatexproducts.com.au